



## **WOVEN TAPE TECHNICAL DATA SHEET**

Product Reference: TVU 600

Characteristics		Nominal	Tolerance	Normative	
Mass per unit area	g/m²	635	± 5%	ISO 4605	
Weave		Plain		ISO 2113	
Standard Width	mm	From 10 mm to 200 mm	± 2,5%		
Laminate Thickness	mm	0,66	± 2,5%	ISO 5084(**)	

Nominal Construction		Warp			Weft		
Fibre Description		Glass Roving 1200 tex		Glass Fibre EC 9 136 tex			
Thread Count	ends/cm		5,0	ISO 4602	1	,2 x 2	ISO 4602
Weight Distribution	g/m² %		Glass Roving	600 95%	1	Glass Fibre	33 5%

(\*\*) Theorical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ