ISO 9001 - Cert No 10490

CristexCompositeMaterials
COMPOSITES YOU CAN TRUST

TECHNICAL DATA SHEET

SAP No. 30005821 **Article Description** X-C-302g/m²-1400mm

Textile Structure 7006087

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	**Construction**	**Areal weight**	**Tolerance**	**Material**
2	-45 °	149 g/m²	+/- 5 %	TORAY T700SC 50C 12K -
1	45 °	149 g/m²	+/- 5 %	TORAY T700SC 50C 12K -
Stitching		4 g/m²	+/- 1 %	PES (Polyester) 48 dtex SC

FURTHER CHARACTERISTICS					
Gauge	5,0	**Stitching pattern**	warp	**Width (nominal)**	1,400 mm
Stitch length	2,60 mm	**Total tolerance**	5,3 %	**Total areal weight**	302 g/m²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.

Cristex Composite Materials

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ

T: 01282 770666 | E: sales@cristex.co.uk | W: www.cristex.co.uk

cristexltd Cristex Composites Cristex Composite Materials