



## Product Information

Resin	Hardener	Mixing ratio by weight
EC 152	W 152 MLR	100:30

**Description:** High performance un-filled epoxy laminating resin, suitable for the moulding of carbon fibre, glass fibre and aramid / kevlar fabrics. A wide variety of hardeners allow for desired pot life's and gel times to be achieved. This laminating resin will cure at room temperature, although it is recommended that a post cure is done at a higher temperature to obtain the best mechanical performance from the resin. As well as its high mechanical properties this resin cures clear so it is suitable for both structural and cosmetic applications.

### Uncured Properties

	Resin (EC152)	Hardener (W152MLR)
<b>Colour</b>	Pale / Yellow	Pale / Yellow
<b>Viscosity @ 25°C</b>	1200 – 1800 mPas	5 – 20 mPas
<b>Density @ 25°C</b>	1.13 – 1.17 g/ml	0.90 – 0.95 g/ml

### Cured Properties

	EC 152 / W 152 MLR
<b>Density @ 25°C</b>	1.08 – 1.12 g/ml
<b>Hardness @ 25°C</b>	84 – 88 Shore D/15
<b>Glass transition (Tg)</b>	82 – 88 °C
<b>Flexural strength</b>	103 – 117 MPa
<b>Maximum strain</b>	5 – 7 %
<b>Strain at break</b>	20 – 30 %
<b>Flexural elastic modulus</b>	2600 – 3200 MPa
<b>Tensile strength</b>	70 – 80 MPa
<b>Elongation at break</b>	6 – 10 %
<b>Compressive strength</b>	85 – 95 MPa



ISO 9001 - Cert No 10490


**CristexCompositeMaterials**  
 COMPOSITES YOU CAN TRUST

### Processing Data:

	Pot Life @ 25°C (50mm / 200ml)	Exothermic Peak @ 25°C (50mm / 200ml)	Gelation Time @ 25°C (1mm)
<b>EC152 / W152MLR</b>	95 – 115 minutes	190 °C – 210 °C	8.5h – 10.5h

### How to use:

Mix 100 parts resin to 30 parts of hardener by weight, this is very important as with all epoxies incorrect mixing ratios will result in a very poor cure of the resin.

Mix thoroughly for at least a minute.

This epoxy system is highly reactive and once mixed will start to exotherm, start lamination of the part as soon as the resin has been properly mixed.

### Demoulding Information

	<b>EC157 / W152MR</b>
<b>Temperature</b>	@ 25 °C (15ml / 6mm)
<b>Demoulding Time</b>	20 – 30h

### Cure / Post Cure Information:

Cristex' epoxy laminating system will cure at room temperature, after demoulding it will take several days for the cure to complete. In order to achieve the best mechanical properties from the resin a post cure is recommended. For most applications a post cure at 50°C is enough however by slowing down the ramp rate or increasing the part cure temperature to 80°C or 90°C this will improve the mechanical performance of the finished part.

### Storage

Epoxy resins and hardeners have a shelf life of two years in the original sealed containers stored in a cool, dry place. The hardeners are moisture sensitive, therefore it is good practice to close the vessel immediately after each use.

### Handling precautions

Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

*Disclaimer:* The information given in this publication is based on the present state of our technical knowledge, buyers and users should make their own assessments of our products under their own application conditions.

