



WOVEN TAPE TECHNICAL DATA SHEET

Product Reference: TKB 170

Characteristics		Nominal	Tolerance	Normative
Mass per unit area	g/m ²	170	± 5%	ISO 4605
Weave		Plain		ISO 2113
Standard Width	mm	From 10 mm to 200 mm	± 2,5%	
Laminate Thickness	mm	0,19	± 2,5%	ISO 5084(**)

Nominal Construction		Warp		Weft	
Fibre Description		Aramid Twaron 2200 – 1210 dtex		Aramid Twaron 2200 – 1210 dtex	
Thread Count	ends/cm	7,0	ISO 4602	3,5 x 2	ISO 4602
Weight Distribution	g/m ²	Aramid Twaron	85	Aramid Twaron	85
	%		50%		50%

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.