

## TECHNICAL DATA SHEET

**SAP No.** 30000335      **Article Description** Q-E-635gm<sup>2</sup>-1270mm

**Textile Structure** 7000166

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	0 °	59 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
4	0 °	118 g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
3	45 °	156 g/m <sup>2</sup>	+/- 5 %	E-glass 200 TEX
2	90 °	134 g/m <sup>2</sup>	+/- 5 %	E-glass 200 TEX
1	-45 °	156 g/m <sup>2</sup>	+/- 5 %	E-glass 200 TEX
Stitching		12 g/m <sup>2</sup>	+/- 3 %	PES (Polyester) 76 dtex

Fibre input can be determined individually

### FURTHER CHARACTERISTICS

<b>Gauge</b>	10,0	<b>Stitching pattern</b>	Tricot-warp	<b>Width (nominal)</b>	1270 mm
<b>Stitch length</b>	2,60 mm	<b>Total tolerance</b>	5,4 %	<b>Total areal weight</b>	635 g/m <sup>2</sup>

#### Labelling (Standard)

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

#### Packaging (Standard)

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

#### Storage

With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.