

## TECHNICAL DATA SHEET

**SAP No.** 30000341      **Article Description** Q-E-986g/m<sup>2</sup>-1270mm

**Textile Structure** 7000171

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	Construction	Areal weight	Tolerance	Material
4	0 °	236 g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
3	45 °	251 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
2	90 °	236 g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
1	-45°	251 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
Stitching		12 g/m <sup>2</sup>	+/- 3 g/m <sup>2</sup>	PES (Polyester) 76 dtex

FURTHER CHARACTERISTICS					
Gauge	10,0	Stitching pattern	Tricot- warp	Width (nominal)	1270 mm
Stitch length	2.60 mm	Total tolerance	5,2 %	Total areal weight	986 g/m <sup>2</sup>

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.