



TECHNICAL DATA SHEET

SAP No: 30000345 Article Description: Y-E-625gm²-1270mm

Textile Structure: 7000173

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)									
Layout	Construction	Areal weight		Tolerance	Material				
3	0°	213	g/m²	+/- 5 %	E-Glass 600 tex				
2	45°	200	g/m²	+/- 5 %	E-Glass 300 tex				
1	-45°	200	g/m²	+/- 5 %	E-Glass 600 tex				
Stitching 12		12	g/m²	+/- 3 g/m ²	PES [Polyester] 76 dtex				

Fibre input can be determined individually

FURTHER CHARACTERISTICS									
Gauge	10,0	Stitching pattern	Tricot - Warp	Width (nominal)	1,270 mm				
Stitch Length	2,60 mm	Total tolerance	5,4 %	Total area weight	625 g/m²				

Labelling (Standard)

Packaging (Standard)

Storage

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ

T: 01282 770666 | E: sales@cristex.co.uk | W: www.cristex.co.uk

CristexItd I Cristex Composites in Cristex Composite Materials