

## TECHNICAL DATA SHEET

**SAP No.** 30000408      **Article Description** X-E-444g/m<sup>2</sup>-1270mm

**Textile Structure** 7000204

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	Construction	Areal weight	Tolerance	Material
4	45 °	217 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
3	90 °	3 g/m <sup>2</sup>	+/- 5 %	E-glass 68 TEX
2	0 °	1 g/m <sup>2</sup>	+/- 5 %	E-glass 68 TEX
1	-45 °	217 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
Stitching		6 g/m <sup>2</sup>	+/- 1 %	PES (Polyester) 76 dtex

FURTHER CHARACTERISTICS					
<b>Gauge</b>	5,0	<b>Stitching pattern</b>	warp	<b>Width (nominal)</b>	1.270 mm
<b>Stitch length</b>	2,60 mm	<b>Total tolerance</b>	5,2 %	<b>Total areal weight</b>	444 g/m <sup>2</sup>

### Labelling (Standard)

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

### Packaging (Standard)

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

### Storage

With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.