



TECHNICAL DATA SHEET

SAP No. 30007135 **Article Description** B-S-E-931g/m²-1270mm

Textile Structure 7000077

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)								
Layer	Construction	Areal weight	Tolerance	Material				
3	0°	331 g/m²	+/- 5 %	E-glass 1.200 TEX				
2	90°	288 g/m²	+/- 5 %	E-glass 600 TEX				
1	CSM	300 g/m²	+/- 10 %	E-glass				
Stitching		12 g/m²	+/- 3 g/m²	PES (Polyester) 110 dtex				

FURTHER CHARACTERISTICS							
Gauge	7,0	Stitching pattern	Tricot-warp	Width (nominal)	1270mm		
Stitch length	3,50mm	Total tolerance	+/- 6,9 %	Total areal weight	931 g/m ²		

Labelling (Standard) Every roll is equipped with a label in the core. A further label is

located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil.

Further packaging options can be determined individually.

Storage With original packaging: Temperature 15-35°C and 20-80%

humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of

storage conditions.