

## TECHNICAL DATA SHEET

**SAP No.** 30007788      **Article Description** SAERcore B 200-PP18-200-587g/m<sup>2</sup>-1250mm

**Textile Structure** 7006259

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	Construction	Areal weight	Tolerance (+/- %)	Material
3	CSM	200 g/m <sup>2</sup>	+/- 10 %	E-Glass
2	Core	180 g/m <sup>2</sup>	+/- 10 %	Polypropylene
1	CSM	200 g/m <sup>2</sup>	+/- 10 %	E-Glass
Stitching		7 g/m <sup>2</sup>	+/- 2 g/m <sup>2</sup>	Polyamid 6.6 122 dtex

Further Characteristics					
<b>Gauge</b>	3.5	<b>Stitching pattern</b>	Tricot	<b>Width</b>	1250 mm
<b>Stich length</b>	5 mm	<b>Total tolerance</b>	+/- 10.2 %	<b>Total areal weight</b>	587 g/m <sup>2</sup>

### Labelling (Standard)

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

### Packaging (Standard)

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

### Storage

With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.

### Important advice

The Z side of the stitching line should be placed preferably on the cosmetic face to obtain the best surface finish.