

TECHNICAL DATA SHEET

SAP No. 30008091 **Article Description** SAERflow BE-600-BX304-150-1270mm

Textile Structure 7008069

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	Construction	Areal weight	Tolerance	Material
7	0°	283 g/m ²	+/- 5 %	E-glass 1.200 TEX
6	90°	283 g/m ²	+/- 5 %	E-glass 600 TEX
5	0°	10 g/m ²	+/- 5 %	E-glass 34 TEX
4	45°	134 g/m ²	+/- 10 %	Hybrid Glass 380 TEX
3	0°	10 g/m ²	+/- 5 %	E-glass 34 TEX
2	-45°	134 g/m ²	+/- 10 %	Hybrid Glass 380 TEX
1	CSM	150 g/m ²	+/- 10 %	E-Glass
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

Fibre input can be determined individually

FURTHER CHARACTERISTICS					
Gauge	5	Stitching pattern	Tricot	Width (nominal)	1270 mm
Stich length	2,60 mm	Total tolerance	+/- 7,1 %	Total areal weight	1010 g/m ²

Tracer yarn¹ 3 PC light brown

¹Position can be determined individually

Labelling (Standard)

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard)

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage

With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.