



TECHNICAL DATA SHEET

Article Description X-E-302g/m²-1270mm **SAP No.** 30009055

Textile Structure 7008669

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)							
Layer	Construction	Areal weight	Tolerance	Material			
4	45 °	145 g/m²	+/- 5 %	E-glass 200 TEX			
3	90 °	4 g/m²	+/- 5 %	E-glass 68 TEX			
2	0 °	2 g/m²	+/- 5 %	E-glass 68 TEX			
1	-45 °	145 g/m²	+/- 5 %	E-glass 200 TEX			
Stitching		6 g/m²	+/- 1 g/m²	PES (Polyester) 76 dtex			

FURTHER CHARACTERISTICS								
Gauge	5,0	Stitching pattern	warp	Width (nominal)	1270 mm			
Stitch length	3,00 mm	Total tolerance	+/- 5,2 %	Total areal weight	302 g/m ²			

Every roll is equipped with a label in the core. A further label is Labelling (Standard)

located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil.

Further packaging options can be determined individually.

Storage With original packaging: Temperature 15-35°C and 20-80%

humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of

storage conditions.