



## TECHNICAL DATA SHEET

## 92115-LS

Style 92115-LS is a woven medium weight glass fibre fabric, it is used for composite manufacture after finishing. It can also be used as a base fabric for coating and or laminating with a diverse range of materials.

## Technical data:

Base Fabric			Tolerance	Test Methods
Yarn	Warp Weft	EC9 – 68 x 3 EC9 - 204	<u>+</u> 5%	DIN EN 12654
Thread Count	Warp Weft	7.0 per 1 cm 6.5 per 1 cm	<u>+</u> 5%	DIN EN 1049
Tensile Strength (typical)	Warp Weft	800 N/cm 700 N/cm		DIN ISO 4606
Weight		280 g/m²	<u>+</u> 5%	DIN EN 12127
Thickness (typical)		0.22 mm		DIN ISO 4603
Weave		Plain		DIN ISO 9354
Composition				
Loss on ignition (Typical) <3%				DIN ISO 1887

Important - Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. It should be noted that the substrate test materials are generic and actual results may vary from those given above. Purchasers should independently determine prior to use the suitability of this material for their specific purposes.

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ

