



WOVEN FABRIC TECHNICAL DATA SHEET

Product Reference: GDc 210 P Blue

Characteristics		Nominal	Tolerance	Normative		
Nass per unit area	g/m²	206	± 5%	ISO 4605		
Weave		Plain		ISO 2113		
Width	mm	1000	± 2,5%			
Thickness	mm	0.21	± 15%	ISO 5084(**)		
Other information		Loomstate				

Nominal Construction		Warp		Weft				
Fibre Description		3K Carbon Fibre 200 tex		Blue Polyester 1100 dtex				
Thread Count	ends/cm	4.8 ISO 4602		10.00 ISO 4602				
Weight	g/m²	3K Carbon Fibre	96	Blue Polyester	110			
Distribution	%	200 tex	47%	1100 dtex	53%			
Weight Rate		47%		53%				

(**) Theorical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ

T: 01282 770666 ~|~ E: sales @cristex.co.uk ~|~ W: www.cristex.co.uk

CristexItd Cristex Composites in Cristex Composite Materials