



WOVEN FABRIC TECHNICAL DATA SHEET

Product Reference: GDc 210 P Green

Characteristics		Nominal Tolerance		Normative		
Mass per unit area	g/m²	206	± 5%	ISO 4605		
Weave		Plain		ISO 2113		
Width	mm	1000	± 2,5%			
Thickness	mm	0.21	± 15%	ISO 5084(**)		
Other information		Loomstate				

Nominal Construction		Warp		Weft		
Fibre Description		3K Carbon Fibre 200 tex		Green Polyester 1100 dtex		
Thread Count	ends/cm	4.8 ISO 4602		10.0	ISO 4602	
Weight	g/m²	3K Carbon	96	Green Polyester	110	
Distribution	%	Fibre 200 tex	47%	1100 dtex	53%	
Weight Rate		47%		53%		

^(**) Theorical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.