



## **WOVEN FABRIC TECHNICAL DATA SHEET**

Product Reference: GG 206 P

Characteristics		Nominal	Tolerance	Normative	
Mass per unit area	g/m²	200	± 5%	ISO 4605	
Weave		Plain	01	ISO 2113	
Width	mm	1000/1200	± 2,5%	ISO 22198	
Thickness	mm	0,16	± 2,5%	ISO 5084(**)	
Other information		Loomstate			

Nominal Construction		Warp		Weft	
Fibre Description		HR Carbon Fibre 3K - 200 tex		HR Carbon Fibre 3K - 200 tex	
Thread Count	ends/cm	5,0	ISO 4602	5,0	ISO 4602
Weight	g/m²	3K	100	3K	100
Distribution	%	Carbon	50%	Carbon	50%
Selvedges		Weaving style	Leno	Type of fibre	HM polyester 22 tex

<sup>(\*\*)</sup> Theorical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.